

## ECC3050S

### Description

ECC3050S conformal coating is a low viscosity, solventless silicone coating that cures very rapidly, at room temperature, to a soft, transparent silicone rubber. ECC3050S conformal coating can also be cured using a low temperature oven process to reduce cure and handling times, making it an excellent candidate to consider for high volume production conformal coating of printed circuit board assemblies with temperature limited components.

### Key Features and Typical Benefits

- Fast Curing - typically ready to handle in just minutes
- Solventless Formulation
- Low Temperature Cure - room/low temperature cure (<60°C)
- Low Viscosity - may be used in many spray or flow coating applications
- Excellent Adhesion - outstanding long-term moisture protection
- Low Modulus/Low Stress - minimizes coating-induced CTE stress to sensitive components

### Typical Physical Properties

TYPICAL UNCURED PROPERTIES	
Viscosity, at 23°C [mPa•s]	550
Tack-Free Time <sup>(1)</sup> , minutes (@ 23°C/73°F, 50% RH)	5
Cure Time <sup>(1)</sup> , minutes (@ 23°C/73°F, 50% RH)	30
Cure Time <sup>(1)</sup> , minutes (@ 60°C/140°F, 15% RH)	2

(1) 100µm (4 mils) thickness

TYPICAL CURED PROPERTIES (3 days @ 23°C/73°F, 50% RH)	
Appearance	Transparent
Specific Gravity (23°C)	0.98
Hardness - Type A	22
Volume Resistivity MW•m {ohm•cm}	1x10 <sup>7</sup> {1x10 <sup>15</sup> }
Dielectric Strength kV/mm (v/mil)	20 (508)
Dielectric Loss (@ 60Hz)	0.001

Dielectric Constant (@ 60Hz)	2.60
------------------------------	------

Typical properties are average data and are not to be used as or to develop specifications.

### **Processing Considerations**

#### **Surface Preparation**

The cleanliness of the circuit board substrate is critical to successful application of the conformal coating and its long-term performance. Surfaces must be free of moisture, dirt, wax, grease and other contaminants. Failure to remove contamination can lead to long-term failure of the circuit assembly.

#### **Solder Flux**

Solder flux residues on the surface of a printed circuit board can greatly impact the performance of a conformal coating by interfering with coating adhesion and possibly interfering with the coating's cure mechanism. This is of particular concern when using 'no-clean' flux systems. Careful compatibility testing, with the flux system to be used, is strongly recommended.

#### **Application Method**

ECC3050S conformal coating can be applied by spray or flow coating. Because ECC3050S conformal coating reacts with atmospheric moisture, dip coating and brush coating are not recommended for volume production operations. The use of atmospherically controlled application equipment is strongly recommended in order to maximize available work life. Spray coating should be done in an enclosed and ventilated area.

#### **Curing**

ECC3050S conformal coating typically cures under room temperature conditions. Depending upon ambient conditions, coated circuit boards may be cured in as little as 30 minutes. The use of a low temperature oven cure (<60°C) may significantly reduce cure/handling times to as little as three minutes. Curing should be done in a ventilated oven. Actual cure time at a given temperature for a given part is dependent upon a variety of factors, including applied thickness of coating, heat sink characteristics of the part being coated, type of oven (i.e. convection, IR, etc.), and oven loading factors. For more detailed information of the curing properties of ECC3050S conformal coating, contact Momentive Performance Materials.

Many of Momentive's materials may meet the requirements for homogeneous materials under 2002/95/EC (RoHS). Please contact Momentive for additional information.

#### **Patent Status**

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

#### **Product Safety, Handling and Storage**

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at [www.momentive.com](http://www.momentive.com) or, upon

request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

**Limitations**

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Copyright 2009-2013 Momentive Performance Materials Inc. All rights reserved.

**Contact Information**

For product prices, availability, or order placement, contact our customer service at [Momentive.com/contact/customer-service](http://Momentive.com/contact/customer-service)

For literature and technical assistance, visit our website at: [www.momentive.com](http://www.momentive.com)

**DISCLAIMER:**

**THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.**

Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

**Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.**